


CICLO DE SINTERIZACION

Polidental Zaragoza s.l c/Leopoldo Romeo 15-17 Zaragoza 50002. España Tlf: +34 976 070 334

www.polidental.com



No.	Temperatura °C	Tiempo (min)
1	0-900	180
2	900-1500	240
3	1500-1500	120
4	1500-0	?